

Technical Information

40-10 | 2K Panel Clear



1. Properties

MS clear for baslac basecoat 35-,

- Easy and safe to spray, fast drying, easy to polish
- To be used on: 1 or 2 vertical panels
- Multi-colored paint jobs, signwriting and plastic parts

2. Application

	Mixing ratio 2 : 1 + 10-30%	100% by vol. 50% by vol. 10 – 30 by vol.	40-10 50-20, -15, -30 60-10, -20, -30, 40
	Spray viscosity DIN 4 at 20°C	16 s	
	Potlife	4 h / 20°C	
	High pressure spray gun	1.3 – 1.4 mm	
	Number of spray coats Film thickness	2 – 3 50 – 60 µm	

3. Drying

	Drying at 20°C	Tack free 2 h	Polishable 4 h
	at 60°C	-	20 min.
	Infrared: (short wave) (medium wave)	8 min. 10 – 15 min.	

Safety instructions:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.