

## 20U-25 2K Black Urethane Primer as a Sealer

### 1. Properties / Information





- 20U-25 2K Black Urethane Primer is a performance sealer that provides good filling properties and quick drying with good melt-in and topcoat holdout. Do **not** mix with 20U-24 2K Grey Urethane Primer.

### 2. Surface Preparation

Substrate/Pretreatment:	Cleaning	Sanding	Second Cleaning
Well cured old paint work	70U-15 Degreaser	P240 - P400 grit	70U-10 Cleaner
O.E.M. primed spare parts	70U-15 Degreaser	P240 - P400 grit	70U-10 Cleaner
Bare steel	70U-15 Degreaser <i>Then, pre-prime with 23U-10 or 25U-30</i>	P80 - P180 grit	70U-10 Cleaner
Galvanized Steel	70U-15 Degreaser <i>Then, pre-prime with 23U-10 or 25U-30</i>	Coarse scuff pad	70U-10 Cleaner
Aluminum	70U-15 Degreaser <i>Then, pre-prime with 23U-10 or 25U-30</i>	P120 - P180 grit	70U-10 Cleaner
Flexible plastic parts	70U-20 Cleaner <i>Then, pre-prime with 21-20</i>	P220 grit	70U-10 Cleaner
Fiberglass, rigid plastic parts (without gelcoat)	70U-15 Degreaser	P220 grit	70U-10 Cleaner

**NOTES:** On Galvanized Steel and Aluminum, make sure sanding is not so vigorous that it removes the galvanized coating. With the second cleaning, make sure all residue is removed. Pay special attention when cleaning Galvanized Steel and Aluminum.







### 3. Application

	<b>Mixing ratio</b>	<b>6:1:2</b> 6 parts 20U-25 1 part 50U-15, 50U-20 or 50U-30 2 parts 60U-10, 60U-20, 60U-30 or 60U-40	<b>Flexed - 4:1:1:2</b> 4 parts 20U-25 1 part 80U-10 1 part 50U-15, 50U-20 or 50U-30 2 parts 60U-10, 60U-20, 60U-30 or 60U-40
	<b>Pot life at 68°F / 20°C</b>	75 - 90 minutes	75 - 90 minutes
	<b>Spray viscosity Ford 4 at 68°F / 20°C</b>	13 - 16 s	14 - 17 s
	<b>Spray gun HVLP</b>	1.3 - 1.5 mm	1.3 - 1.5 mm
	<b>Spray pressure HVLP at the cap</b>	6 - 10 psi	6 - 10 psi
	<b>Application</b>	1 - 2 medium wet coat	1 - 2 medium wet coat
	<b>Film thickness</b>	1.0 - 1.5 mil	1.0 - 1.5 mil
	<b>Coverage</b>	601 sq. ft./gal @ 1.0 mil	629 sq. ft./gal @ 1.0 mil

# Undercoat Technical Information

## 20U-25 2K Black Urethane Primer as a Sealer

### 4. Flash off / Drying / Sanding

	Flash-off at 68°F / 20°C	5 minutes between coats	5 minutes between coats
	Drying at 68°F / 20°C at 140°F / 60°C	30 minutes flash before topcoating N/A	30 minutes flash before topcoating N/A
	Infrared short wave medium wave	N/A N/A	N/A N/A
	Wet sand by Hand	N/A	N/A
	Dry sand by Hand	N/A	N/A
	Dry sand by Machine	N/A	N/A

### 5. VOC / Comments

VOC as applied	≤ 550 gms/liter (≤ 4.6 lbs/gal)	≤ 550 gms/liter (≤ 4.6 lbs/gal)
Comments	Do <b>not</b> mix with 20U-24 2K Grey Urethane Primer.	

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous & should be used according to label directions & technical data information. Appropriate respiratory protection should be worn at all times while products are in use — read product label and Safety Data Sheet (SDS) for specific details. Statements & methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only & are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.