

20U-23 2K White Urethane Primer as a Primer Surfacer

1. Properties / Information





- 20U-23 2K White Urethane Primer is a quick cure, sandable primer that provides good sand scratch filling with excellent adhesion and topcoat holdout. Do **not** mix with 20U-24 2K Grey Urethane Primer.

2. Surface Preparation

Substrate/Pretreatment:	Cleaning	Sanding	Second Cleaning
Well cured old paint work	70U-15 Degreaser	P240 - P400 grit	70U-10 Cleaner
O.E.M. primed spare parts	70U-15 Degreaser	P240 - P400 grit	70U-10 Cleaner
Bare steel	70U-15 Degreaser <i>Then, pre-prime with 23U-10 or 25U-30</i>	P80 - P180 grit	70U-10 Cleaner
Galvanized Steel	70U-15 Degreaser <i>Then, pre-prime with 23U-10 or 25U-30</i>	Coarse scuff pad	70U-10 Cleaner
Aluminum	70U-15 Degreaser <i>Then, pre-prime with 23U-10 or 25U-30</i>	P120 - P180 grit	70U-10 Cleaner
Flexible plastic parts	70U-20 Cleaner <i>Then, pre-prime with 21-20</i>	P220 grit	70U-10 Cleaner
Fiberglass, rigid plastic parts (without gelcoat)	70U-15 Degreaser	P220 grit	70U-10 Cleaner

NOTES: On Galvanized Steel and Aluminum, make sure sanding is not so vigorous that it removes the galvanized coating. With the second cleaning, make sure all residue is removed. Pay special attention when cleaning Galvanized Steel and Aluminum.







3. Application

	Mixing ratio	6:1:1 6 parts 20U-23 1 part 50U-15, 50U-20 or 50U-30 1 part 60U-10, 60U-20, 60U-30 or 60U-40	Flexed - 4:1:1:1 4 parts 20U-23 1 part 80U-10 1 part 50U-15, 50U-20 or 50U-30 1 part 60U-10, 60U-20, 60U-30 or 60U-40
	Pot life at 68°F / 20°C	60 - 75 minutes	60 - 75 minutes
	Spray viscosity Ford 4 at 68°F / 20°C	14 - 17 s	15 - 18 s
	Spray gun HVLP	1.5 - 1.7 mm	1.5 - 1.7 mm
	Spray pressure HVLP at the cap	6 - 10 psi	6 - 10 psi
	Application	2 - 3 medium wet coats	2 - 3 medium wet coats
	Film thickness	2.0 - 3.0 mil	2.0 - 3.0 mil
	Coverage	675 sq. ft./gal @ 1.0 mil	727 sq. ft./gal @ 1.0 mil

Undercoat Technical Information

20U-23 2K White Urethane Primer as a Primer Surfacer

4. Flash off / Drying / Sanding

	Flash-off at 68°F / 20°C	5 minutes between coats and before force drying	5 minutes between coats and before force drying
	Drying at 68°F / 20°C at 140°F / 60°C	60 - 90 minutes 30 minutes	60 - 90 minutes 30 minutes
	Infrared short wave medium wave	5 - 7 minutes N/A	5 - 7 minutes N/A
	Wet sand by Hand	P400 grit	P400 grit
	Dry sand by Hand	P320 grit	P320 grit
	Dry sand by Machine	P320 grit	P320 grit

5. VOC / Comments

VOC as applied	≤ 580 gms/liter (≤ 4.8 lbs/gal)	≤ 580 gms/liter (≤ 4.8 lbs/gal)
Comments	Do not mix with 20U-24 2K Grey Urethane Primer.	

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous & should be used according to label directions & technical data information. Appropriate respiratory protection should be worn at all times while products are in use — read product label and Safety Data Sheet (SDS) for specific details. Statements & methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only & are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.